

MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

THE PERSON OF TH



THEORY OF VISCOPLASTIC SHELLS FOR DYNAMIC RESPONSE

Weidlinger Associates, Consulting Engrg 333 Seventh Ave New York, New York 10001

1 January 1982

chnical Report

131272

CONTRACT No. DNA 001-81-C-0048

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.

THIS WORK WAS SPONSORED BY THE DEFENSE NUCLEAR AGENCY UNDER RDT&E RMSS CODE B344081466 Y99QAXSF00002 H2590D.

FILE COPY

Prepared for
Director
DEFENSE NUCLEAR AGENCY
Washington, DC 20305



88 08 02 003

Destroy this report when it is no longer needed. Do not return to sender.

PLEASE NOTIFY THE DEFEASE NUCLEAR AGENCY, ATTN: STTI, WASHINGTON, D.C. 20305, IF YOUR ADDRESS IS INCORRECT, IF YOU WISH TO BE DELETED FROM THE DISTRIBUTION LIST, OR IF THE ADDRESSEE IS NO LONGER EMPLOYED BY YOUR ORGANIZATION.

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
T. REPORT NUMBER DNA-TR-81-50	AIBI 272	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) THEORY OF VISCOPLASTIC SHELLS FOR DYNAMIC		5. TYPE OF REPORT & PERIOD COVERED Technical Report
RESPONSE		PERFORMING ORG. REPORT NUMBER CONTRACT OR GRANT NUMBER(#)
R. S. Atkatsh M. P. Bieniek I. S. Sandler		•DNA 001-81-C-0048
9. PERFORMING ORGANIZATION NAME AND ADDRESS Weidlinger Associates, Consulting E 333 Seventh Avenue New York, New York 10001	ingrg	Task Y99QAXSF-00002
Director Defense Nuclear Agency Washington, DC 20305		12. REPORT DATE 1 January 1982 13. NUMBER OF PAGES 68
14. MONITORING AGENCY NAME & ADDRESS(II different	from Controlling Office)	15. SECURITY CLASS (of this report) UNCLASSIFIED 15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report)		N/A

Approved for public release; distribution unlimited.

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

18. SUPPLEMENTARY NOTES

CALIFOLIA LABORARIO VERRESCE VICELISTE MOSCOLO MONOMEN INTERESCENT MANAGEMENT MANAGEMENT

This work was sponsored by the Defense Nuclear Agency under RDT&E RMSS Code B344081466 Y990AXSF00002 H2590D.

19. KEY WORDS (Continue on reverse side if necessary and identify by block number)

Viscoplasticity Dynamic Response Shell Analysis EPSA Finite Element Code Strain Rate Effects

O. ABSTRACT (Continue on reverse side if necessary and identify by block number)

Viscoplastic shell model is formulated which utilizes the shell membrane strains and curvatures as the kinematic variable and the shell stress resultants as the dynamic variables.

The viscoplastic shell model combines the concept of Perzyna's viscoplastic constitutive equations with Bieniek's shell stress resultant formulation. model is incorporated into the EPSA code for the analysis of shells in an

DD 1 FORM 1473

EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

30. ABSTRACT (Continued)
acoustic medium subjected to dynamic loading which produce large elasto- viscoplastic deformations in the shell. Several examples are presented to exhibit the effect of material rate dependence upon structural response.
,

Conversion factors for U.S. customary to metric (SI) units of measurement

To Convert From	То	Multiply By
angstrom	meters (m)	1. 000 000 X E -10
atmosphere (normal)	kilo pascal (kPa)	1.013 25 X E +2
bar	kilo pascal (kPa)	1. 000 000 X E +2
barn	meter ² (m ²)	1. 000 000 X E -28
British thermal unit (thermochemical)	joule (J)	1. 054 350 X E +3
calorie (thermochemical)	joule (J)	4. 184 000
cal (thermochemical)/cm ²	mega joule/m ² (MJ/m ²)	4. 184 000 X E -2
curie	giga becquerei (GBq)	3.700 000 X E +1
degree (angle)	radian (rad)	1. 745 329 X E -2
degree Fahrenheit	degree kelvin (K)	$t_{\mu} = (t^{\circ}f + 459.67)/1.8$
electron volt	joule (J)	1.602 19 X E -19
•15	joule (J)	1. 000 000 X E ~7
erg/second	watt (W)	1. 000 000 X E -7
foot	meter (m)	3. 048 000 X E -1
foot-pound-force	joule (J)	1. 355 818
gailon (U.S. liquid)	meter ³ (m ³)	3. 785 412 X E -3
tach	meter (m)	2. 540 000 X E -2
jerk	joule (J)	1. 000 000 X.E +9
joule/kilogram (J/kg) (radiation dose absorbed)	Gray (Gy)	1,000 000
kilotons	terajoules	4. 183
kip (1000 lhf)	pervices (N)	4, 448 222 X E +3
kip/inch ² (kat)	kilo pascal (kPa)	6, 894 757 X E +3
ktap	newton-second/m ² (N-s/m ²)	1, 000 000 X E +2
micron	meter (m)	1.000 000 X E -6
mil	meter (m)	2, 540 000 X E -5
mile (international)	meter (m)	1. 609 344 X E +3
ounce	kilogram (kg)	2. 834 952 X E -2
pound-force (lbs avoirdupols)	newton (N)	4. 448 222
pound-force tach	newton-meter (N·m)	1. 129 848 X E -1
pound-force/tach	newton/meter (N/m)	1. 751 268 X E +2
pound-force/foot ²	idio pascal (kPa)	4. 788 026 X E -2
pound-force/tach ² (psi)	kilo pascal (kPa)	6. 894 757
pound-mass (lbm avoirdupois)	kilogram (kg)	4, 535 924 X E -1
pound-mass-foot ² (moment of inertia)	kilogram-meter ² (kg·m ²)	4. 214 011 X E -2
pound-mass/foot ³	kilogram/meter ³ (lag/m ³)	
rad (radiation dose absorbed)	••Gray (Gy)	1.601 846 X E +1 1.000 000 X E -2
roentgen	coulomb/kilogram	
shales	(C/lig)	2. 579 760 X E -4
sing	second (s)	1.000 000 X E -8
torr (mm Hg, 0°C)	kilogram (kg)	1. 459 390 X E +1
(tag, v c/	kilo pascal (kPa)	1. 333 22 X E -1

[&]quot;The becquerel (Bq) is the SI unit of radioactivity; 1 Bq = 1 event/s.
"The Gray (Gy) is the SI unit of absorbed radiation.

CHARLES CHARLES CHARLES CHARLES CONTROL CHARLES CHARLES

TABLE OF CONTENTS

<u>se</u>	ctior		Page
		LIST OF ILLUSTRATIONS	4
	I	INTRODUCTION	5
	II	SURVEY OF EXISTING VISCOPLASTIC THEORIES AND THEIR USE IN SHELL ANALYSIS	8
	III	MATERIAL CONSTITUTIVE EQUATIONS	12
	IV	SHELL CONSTITUTIVE EQUATIONS	
		a. THROUGH-THE-THICKNESS INTEGRATION	15
		b. VISCOPLASTIC SHELL MODEL: DIRECT FORMULATION	17
	v	COMPARISON OF THROUGH-THE-THICKNESS AND SHELL MODEL RESULTS FOR THE BEHAVIOR OF MILD STEEL DURING	
		MULTI-DIMENSIONAL LOADING	21
	VI	INCORPORATION OF VISCOPLASTIC SHELL MODEL INTO EPSA CODE	24
	VII	VISCOPLASTIC SHELL ANALYSIS USING EPSA - REPRESENTATIVE EXAMPLES	26
	VIII	CONCLUSIONS	28
		REFERENCES	29

The second teacher transfer to the second second transfer transfer transfer to the second transfer transfer to the second transfer tr

Accession For
NTIS CPA&I
DTIC TAD
Unang smooth
Justif within .
Py
Distribution/
Availability Codes
Avera and/or
Dist Crucial
4



LIST OF ILLUSTRATIONS

Figure		Page
1	Bingham's One Dimensional Viscoplastic Model Representation	33
2	Dynamic Stress-Strain Relation for Elastic Viscoplastic Material in Tension	34
3	One Dimensional Yield Function versus Strain Rate for	24
	Mild Steel	35
4	One Dimensional Yield Stress versus Strain Rate for	
5	Mild Steel - Five Parameter Fit	36
,	Steel - Three Parameter Fit	37
6	Multi-Dimensional Loading Paths chosen for Determination	٠,
	of Viscoplastic Shell Model Parameters	38
7	One Dimensional Force versus Strain for Variable Rate	39
8	One Dimensional Moment versus Curvature for Various Loading	
9	Rates One Dimensional Limit Force and Moment versus Loading Rate	40 41
10	Moment versus Curvature: $\dot{\mathbf{k}} = 120 \text{ 1/sec.}$	41
11	Loading Case No. 4	43
12	Loading Case No. 5a	44
13	Loading Case No. 5b	45
14	Loading Case No. 6	46
15	Loading Case No. 7a	47
16 17	Loading Case No. 7c	48
18	Loading Case No. 7d	49 50
19	Loading Case No. 8	50 51
20	Loading Case No. 9	52
21	Loading Case No. 10	53
22	Loading Case No. 11	54
23	Loading Case No. 12	55
24	Non-linear Transient Response of Cylindrical Panel -	
25	Model Properties EPSA Finite Element Model	56 57
26	Permanent Deflection Along Centerline of Cylindrical Model	58
27	Inner Fiber Hoop Strain at Center of Cylindrical Panel	59
28	Stiffened Cylindrical Shell Model	60
29	Permanent Deflection of Stiffened Cylindrical Shell	61
30	Inner Fiber Hoop Strain of Stiffened Cylindrical Shell	62

I INTRODUCTION

100 Sept. 100 Se

ANAMARIA GERRARIA GERRARIA DESERVATOR

Impact loadings from explosive sources generally deform structural components at high strain rates. These strain rates are manifested via elasto-viscoplastic structural response in many materials such as steel, titanium, and reinforced concrete. It has been shown experimentally that the dynamic load carrying capacities of structures are significantly greater than the corresponding static values. Survey papers of experimental work undertaken to study structural response to impulsive loading have been written by Jones, et. al. [27] and Rawlings [28].

The endeavor to understand and mathematically model the nonlinear, inelastic deformation process has led to various paths of development. From an engineering perspective, concern focuses on establishing techniques which capture the essence of the complex material behavior and are suitable for the analysis of realistically modelled structures. Therefore, this paper discusses the development of an efficient, practical and theoretically sound method of analyzing the dynamic response of structures.

THE STATE OF THE STATES IN BOSCONIES SEASONS IN THE SEASONS IN THE SEASON IN THE SEASON WAS ASSOCIATED AND THE SEASON WAS ASSOCIATED ASSOCIATED ASSOCIATED ASSOCIATED AND THE SEASON WAS ASSOCIATED ASSO

A generalization of the viscoplastic constitutive model as defined by Perzyna [1] has been employed in the formation of a system of equations defining a viscoplastic shell model in the general manner proposed by Bieniek and Funaro [2] for elastoplastic shells. This resulting shell model is then incorporated into the nonlinear finite difference/finite element code EPSA (Elasto-Plastic Shell Analysis), [3], [4]. The shell model

developed in the course of this work utilizes the shell membrane strains and curvatures as the kinematic variables and the shell stress resultants (membrane forces and moments) as the dynamic variables. When compared to the alternative through-the-thickness integration method of calculating stress resultants, this approach offers considerable advantages in terms of both computer storage and speed. Additionally, the model can be fit to experimental data representing various loading combinations (biaxial bending and stretching) at various loading rates on plate and shell specimens.

The shell model approach can also be applied to non-metallic materials. In particular, a reinforced concrete shell model can be formulated, thereby avoiding the difficulties involved in the through-the-thickness approach arising from stress re-distribution due to cracking and debonding.

This paper presents the qualitative and quantitative aspects of the viscoplastic shell model through an examination of a number of multi-dimensional loading combinations at various loading rates for a particular material type. The incorporation of the model into the EPSA code is outlined, and a study is presented of the effects of viscoplastic material response on the dynamic behavior of a cylindrical panel in vacuo and a closed cylinder in an acoustic medium.

It is anticipated that the strain rate-dependent models will be utilized for the analysis of a wide variety of problems of Defense Nuclear Agency interest involving the explosive loading of structures.

II SURVEY OF EXISTING VISCOPLASTIC THEORIES AND THEIR USE IN SHELL ANALYSIS

Continuing research into the viscoplastic behavior of crystalline solids has proceeded from both the microscopic and macroscopic point of view.

Bingham [6] formulated for the case of one dimensional shear a relationship represented by Figure(1). Thic concept was extended to three dimensional states of stress by Hohenemser and Prager [7] with the resulting expression for the plastic strain rate $\dot{\epsilon}_{ij}^{p}$ in the form

$$\dot{\varepsilon}_{ij}^{p} = \frac{1}{2\mu} \frac{\sqrt{J_{2}^{i}} - k}{\sqrt{J_{2}^{i}}} \delta_{ij}$$
 (1)

where J_2' is the second invariant of the deviatoric stress δ_{ij} . (μ and k are material constants).

A generalization of these basic ideas has been developed by Perzyna [1]. Included in the specification is the existence of a quasi-static yield function

$$F = \frac{f(\sigma_{ij}, \epsilon_{ij}^{p})}{\kappa} - 1$$
 (2)

where

$$\kappa = \kappa(W_p) = k \int_{0}^{\varepsilon_{ij}^{p}} \sigma_{ij} d\varepsilon_{ij}^{p}$$
(3)

is the work hardening parameter which describes how the quasistatic yield surface deforms during the inelastic process. The dependence of the plastic strain rate tensor on the stress intensity is given by

$$\dot{\varepsilon}_{ij}^{p} = \gamma \kappa \Phi[F] \frac{\partial f}{\partial \sigma_{ij}}$$
 (4)

where γ and $\Phi[F]$ are material response functions. The direction of

the viscoplastic strain rate vector is directed along the normal to the subsequent dynamic yield surface.

The dependence of the yield criteria on the strain rate and the dynamic yield criteria for elasto-viscoplastic work-hardening materials is given as

$$f(\sigma_{ij}, \epsilon_{ij}^{p}) = \kappa(W_{p}) \left\{ 1 + \Phi^{-1} \left[\frac{(I_{2}^{p})}{\gamma} (\frac{1}{2} \frac{\partial f}{\partial \sigma_{k\ell}} \frac{\partial f}{\partial \sigma_{k\ell}})^{-1/2} \right] \right\}$$
(5)

where

$$I_{2}^{p} = \frac{1}{2} \stackrel{\cdot}{\epsilon}_{ij}^{p} \stackrel{\cdot}{\epsilon}_{ij}^{p} \tag{6}$$

Figure(2) shows a dynamic stress-strain relation for elastic viscoplastic work-hardening material in simple tension.

A mathematical description of the inelastic metal deformation process proposed by Cernocky and Krempl [8] is based upon the following relation for the plastic strain rates

$$\dot{\varepsilon}_{ij}^{p} = C_{ijkl} \frac{\sigma_{kl} - G_{kl}}{\kappa[\Gamma]}$$
 (7)

where C_{ijkl} is the elastic compliance tensor, G_{kl} is the stress tensor corresponding to the "equilibrium stress-strain curve", Γ is the second invariant of $(\sigma_{kl} - G_{kl})$ and $\kappa[\Gamma]$ is a material function.

Motivated by dislocation dynamics, Bodner and Partom[9] proposed a functional relationship between the second invariant of the plastic strain rate D_2^p and the second invariant of the deviatoric stress J_2^t $D_2^p = F[J_2^t]$

of the functional is chosen to reproduce the

(8)

where the form of the functional is chosen to reproduce the stress-strain curves of a particular material.

Werne and Kelly [10] arrived at a model of metal

viscoplasticity from dislocation dynamics considerations

$$\dot{\epsilon}_{ij}^{p} = 8b_{o} \beta n\xi \delta_{ij} \tag{9}$$

where β is a nonlinear function of the deviatoric stress invariant. η and ξ are defined in terms of their evolutionary equations and represent the dislocation density and the mobile fraction, respectively. b_0 is Burger's vector. This model was shown capable of reproducing various types of uniaxial stress-strain curves.

Material models incorporating viscoelastic behavior have also been introduced. Naghdi and Murch [25] have postulated a theory of viscoelastic/plastic solids which reduces to that of linear viscoelasticity and to that of classical plasticity in limiting cases.

Inelastic analysis includes, in addition to a mathematical description of the metal constitutive behavior, a solution scheme for the governing nonlinear equations of motion.

Zirin and Krempl [11] used a finite element technique to solve plane stress, plane strain and axisymmetrical problems incorporating Krempl's [8] viscoplastic model. A particular problem investigated was a thick-walled axisymmetrical cylinder under internal pressure.

Werne and Kelly [10] used the HONDO code [12] response of a cylinder and a bar in uniaxial tension.

A numerical analysis of the elastic viscoplastic response of an axisymmetrical spherical shell was performed by Takezono, et. al. [13] using Perzyna's constitutive model.

The incorporation of the viscoplastic shell model into

the EPSA code for usage in solving three dimensional shell type structural problems required the selection of a general form for the viscoplastic constitutive relations. The representation chosen was based upon Perzyna's model [1]. The governing arguments for this selection were:

- The functional form of the constitutive relations is of sufficient generality so that a broad range of material behavioral patterns could be represented.
- 2. Experimental verification by Hayashi and Tanimoto[26] of a Perzyna type formulation for describing the response of annealed aluminum to impulsive torque and tension loadings.
- 3. Retention by the constitutive model of certain basic elements of the classical theory of plasticity which have proved to be a practical and accurate tool of analysis for elasto-plastic structures. In particular, uniqueness arguments of the type made by Drucker[24] are applicable.
- 4. The model incorporates multi-dimensional stress-strain states including loading and unloading paths.
- A shell model formulation could be established incorporating the material constitutive equations.
- 6. A stable solution scheme for the viscoplastic shell equations could be established.
- 7. The model is effective in capturing complex material behavior while still being cost effective from a computational point of view.

III MATERIAL CONSTITUTIVE EQUATIONS

Perzyna postulated a set of constitutive equations to represent viscoplastic strain hardening behavior for arbitrary loading histories [[1]. Included in this specification is the direction of the viscoplastic strain rate and the magnitude of allowable stress beyond the static yield surface.

The particular case of constitutive relations chosen is that of elastic visco-perfectly plastic material behavior for which the static yield function in stress space is the von Mises yield condition

$$F(s_{ij}) = \frac{1}{2} \frac{s_{ij} s_{ij}}{\kappa^2} - 1$$
 (10)

where δ_{ij} are the deviatoric stresses, $K = \frac{60}{\sqrt{3}}$ and σ_{o} is the uniaxial static yield stress.

The rate of increase of the inelastic components of the strain tensor is a function of the excess stresses beyond the static yield surface(overstress). The direction of the viscoplastic strain rate vector is along the normal to the subsequent loading surface. These relations are mathematically stated as

$$\dot{\varepsilon}_{ij}^{P} = \gamma K \Phi[F(s_{ij})] \frac{\partial F}{\partial s_{ij}} = \bar{\lambda} \frac{\partial \bar{F}}{\partial s_{ij}}$$
(11)

where γ and $\Phi[F]$ are material functions which can be chosen to represent the results of experimental tests on the dynamic behavior of a particular material. Current available experimental methods consist of one-dimensional stress-strain tests performed using a hydropneumatic machine or a hopkinson bar technique [14].

Figure (3) shows a one dimensional yield stress versus strain rate curve. Manjoine [17] states that this "S" shaped curve is

typical of metals tested within a given range of strain rates. The particulars of the curve vary for each material type.

An approximation or fit to this characteristic yield stress versus strain rate curve is made by the following expression

$$\dot{\varepsilon}_{11}^{P} = a_{1}(F)^{1/n_{1}} + \frac{a_{2}(F)^{n_{2}}}{(F_{1} - F)^{n_{3}}}$$
(12)

where

$$F_{L} = \left(\frac{\sigma_{L}}{\sigma_{O}}\right)^{2} - 1 \tag{13}$$

and $\boldsymbol{\sigma}_L^{}$ is a limiting one dimensional yield stress achieved from dynamic tests at the highest of strain rates of interest.

Note that equation (12) can be reduced to either a convex or concave power law (with or without an upper limiting stress) representation of the yield stress versus strain rate behavior. The power law representation has been prevalent in previous works [15] and [16].

This one dimensional experimental data can be represented in Perzyna's formulation by assuming $\Phi[F] = F$ and using a suitable functional form for γ . Then, specializing equation (11) to

one dimensional behavior
$$\dot{\varepsilon}_{11}^{P} = \frac{2}{\sqrt{3}} \quad \gamma \frac{\sigma_{11}}{\sigma_{0}} \quad (\frac{\sigma_{11}^{2}}{\sigma_{0}^{2}} - 1) \tag{14}$$

or in terms of the static yield function F($^\delta_{\ ij}$) $\dot{\epsilon}_{11}^P = \frac{2}{\sqrt{3}} \; \gamma F(\sqrt{F+1})$

$$\dot{\varepsilon}_{11}^{P} = \frac{2}{\sqrt{3}} \gamma_F (\sqrt{F+1}) \tag{15}$$

Equations (12) and (15) state that the material response

function Y is

$$\gamma = \frac{\sqrt{3}}{2} \left[\frac{a_1}{(F)^{1-1/n} 1 \sqrt{F+1}} + \frac{a_2 (F)^{n_2-1}}{(F_L - F)^{n_3} \sqrt{F+1}} \right]$$
 (16)

Appropriate values of the material constants a_1 , a_2 , n_1 , n_2 and n_3 are determined by curve fitting to one dimensional stress-strain rate experimental data.

As an illustrative example, the uniaxial behavior of a mild steel within the strain rate range of $\left(10\right)^0$ to $\left(10\right)^3$ l/sec is investigated.

The experimental data of Clark and Duwez [18] is fit to via the parameter values shown in Figure (4).

The general character of equation (16) is that γ approaches infinity at the asymptotes F = 0 and F = F_L. This behavior can also be represented by the expression

$$\gamma = \frac{\bar{a}_1}{\bar{n}_1(F_L - F)^2} \tag{17}$$

The curve fit and parameter values using equation(17) are shown in Figure (5) for the mild steel material.

IV SHELL CONSTITUTIVE EQUATIONS

Shell structures resist external loading by developing internal biaxial forces and moments. Two alternative computational approaches for obtaining these internal stress resultants are presented.

a. Through-The-Thickness Integration

For this technique, the time increments of strains at any point of the shell are expressed in terms of the strain and curvature increments of the middle shell surface.

$$\Delta_{N} \varepsilon_{ij}(z) = \Delta_{N} \varepsilon_{ij} + \Delta_{N} \kappa_{ij} Z$$
 (18)

The time increments of shell forces and moments(stress resultants) are determined by

$$\Delta_{\mathbf{N}} \mathbf{N}_{\mathbf{i}\mathbf{j}} = \begin{cases} h/2 \\ \Delta_{\mathbf{N}} \sigma_{\mathbf{i}\mathbf{j}} & \mathrm{d}z & \Delta_{\mathbf{N}} M_{\mathbf{i}\mathbf{j}} = \int_{-h/2}^{h/2} \Delta_{\mathbf{N}} \sigma_{\mathbf{i}\mathbf{j}} & z & \mathrm{d}z \end{cases}$$
(19)

The integrals are numerically computed by dividing the shell thickness into "k" layers and assuming a linear stress distribution within each layer.

The stress increments $^{\Delta}_{\ N}{}^{\sigma}_{\ ij}$ are computed from the material constitutive equations

$$\Delta_{\mathbf{N}} \sigma_{\mathbf{i}\mathbf{j}} = \sigma_{\mathbf{i}\mathbf{j}}^{\mathbf{N}} - \sigma_{\mathbf{i}\mathbf{j}}^{\mathbf{N}-1} = C_{\mathbf{i}\mathbf{j}\mathbf{k}\mathbf{l}} \Delta_{\mathbf{N}} (\varepsilon_{\mathbf{k}\mathbf{l}} - \varepsilon_{\mathbf{k}\mathbf{l}}^{\mathbf{p}})$$
 (20)

where σ_{ij}^{N} is the stress tensor after "N" time increments,

 c_{ijkl} is the elastic moduli matrix. The total strain increment to be separated into elastic and inelastic components.

$$\Delta_{N} \varepsilon_{ij} = \Delta_{N} \varepsilon_{ij}^{e} + \Delta_{N} \varepsilon_{ij}^{p}$$
 (21)

Equation (20) may be interpreted as

$$\sigma_{ij}^{N} = \sigma_{ij}^{ElTr} - c_{ijkl} \Delta_{N} \varepsilon_{kl}^{P}$$
 (22)

where σ_{ij}^{ElTr} is the stress tensor based upon a trial assumption of total elastic behavior occurring within the Nth time step.

$$\sigma_{ij}^{ElTr} = \sigma_{ij}^{N-1} + c_{ijkl} \Delta_{N} \epsilon_{kl}$$
 (23)

Writing the viscoplastic relations (equation(11)) in time

incremental fashion

$$\Delta_{N} \epsilon_{ij}^{p} = \Delta t \gamma \ KF(\Delta_{ij}^{N}) \frac{\partial F}{\partial \Delta_{ij}^{N}} = \lambda \frac{\partial F}{\partial \Delta_{ij}^{N}}$$
(24)

λ is a non-negative variable which must be determined as follows;

$$\lambda = \gamma \Delta t KF \left(s_{ij}^{ElTr} - C_{ijkl}^{\Delta} N \varepsilon_{kl}^{p} \right)$$
 (25)

Noting $\frac{\partial F}{\partial_{\delta_{ij}}^{N}} = \frac{\delta_{ij}}{K^2}$ and $C_{ijkl}\delta_{kl} = 2G \delta_{ij}$, Equation (25) becomes,

$$\lambda = \gamma \Delta t KF (s_{ij}^{ElTr} - \frac{2G\lambda}{\kappa^2} s_{ij}^{ElTr})$$
 (26)

Equating arguments of function $F(s_{ij})$ yields,

$$\delta_{ij} = \frac{\delta_{ij}^{E1Tr}}{1 + \frac{2G}{\kappa^2} \lambda}$$
 (27)

and

$$\lambda = \gamma \Delta t K \quad \left(\frac{\frac{1}{2} \delta_{ij}^{ElTr} \delta_{ij}^{ElTr}}{\left(1 + \frac{2G}{2} \lambda\right)^{2} K^{2}} - 1 \right) \quad (28)$$

Rearranging equation (28) gives

$$(\frac{4G^{2}}{K^{2}}) \lambda^{3} + (\frac{4G}{K^{2}} + \frac{4G^{2}\gamma\Delta t}{K^{3}}) \lambda^{2} + (1 + \frac{4G\gamma\Delta t}{K}) \lambda$$

$$-\gamma\Delta tK (F(\delta_{11}^{E1Tr})) = 0$$
(29)

The real root is extracted from a cubic equation solver of λ [γ , Δ t, K , G ,F(σ_{ij}^{ElTr})] = 0 where γ is given as described in Section III.

b. Viscoplastic Shell Model - Direct Formulation

The direct shell model formulation relates the dynamic variables S_{ij} (membrane forces and bending moments) to the kinematic variables e_{ij} (strains and curvatures of the shell's middle surface

$$\mathbf{e}_{ij} = \begin{cases} \varepsilon_{11} \\ \varepsilon_{22} \\ 2\varepsilon_{12} \\ \kappa_{11} \\ \kappa_{22} \\ 2\kappa_{12} \end{cases} \qquad \mathbf{S}_{ij} = \begin{cases} \mathbf{N}_{11} \\ \mathbf{N}_{22} \\ \mathbf{M}_{11} \\ \mathbf{M}_{22} \\ \mathbf{M}_{12} \end{cases}$$
(30)

The quasi-static yield surface in stress resultant space is

$$F(S_{ij}) = I_N + I_N^2 - I_N^3 + I_M^* + 0.8|I_{NM}|$$
 (31)

which describes the current yield surface as the loading path moves from an initial yield surface $F_o(S_{ij})$ towards the limit surface $F_L(S_{ij})$.

$$F_o(S_{ij}) = I_N + I_M + 2 |I_{NM}|$$
 (32)

$$F_L(S_{ij}) = 2 I_N - I_N^2 + \frac{4}{9} I_M$$
 (33)

where I_N , I_M , I_{NM} and I_M are stress resultant invariants defined as

$$I_N = \frac{1}{N_0^2} (N_{11}^2 + N_{22}^2 - N_{11} N_{22} + 3 N_{12}^2)$$

$$I_{M} = \frac{1}{M_{0}^{2}} (M_{11}^{2} + M_{22}^{2} - M_{11}^{2} + 3 M_{12}^{2})$$

$$I_{NM} = \frac{1}{N_0 M_0} (N_{11} M_{11} + N_{22} M_{22} - \frac{1}{2} N_{11} M_{22} - \frac{1}{2} N_{22} M_{11} + 3 N_{12} M_{12})$$

$$I_{M}^{*} = \frac{1}{M_0^{2}} [(M_{11} - M_{11}^{*})^{2} + (M_{22} - M_{22}^{*})^{2}$$
(34)

$$-(M_{11} - M_{11}^*)(M_{22} - M_{22}^*) + 3(M_{12} - M_{12}^*)^2]$$

$$N_0 = \sigma_0 h$$
 , $M_0 = \sigma_0 h^2 / 6$

where σ_0 is the static yield strength.

The quantities $M_{ij}^{}$, which will be referred to as "hardening parameters" are defined by

If
$$F = 1$$
 and $\frac{\partial F}{\partial N_{ij}} \dot{N}_{ij} + \frac{\partial F}{\partial M_{ij}} \dot{M}_{ij} > 0$: $dM_{ij}^{*} = \beta_{ij} (1 - F_L) \frac{M_o}{\kappa_o} \partial \kappa_{ij}^{p}$

If $F < 0$ or $\frac{\partial F}{\partial N_{ij}} \dot{N}_{ij} + \frac{\partial F}{\partial M_{ij}} \dot{M}_{ij} \le 0$: $dM_{ij}^{*} = 0$

(36)

The elastic law

$$S_{ij} = E_{ij\kappa\ell}(e_{k\ell} - e_{k\ell}^{p})$$
(37)

is used where \mathbf{E}_{iikl} is the elastic shell stiffness matrix.

The above quasistatic shell formulation is derived from that proposed by Bieniek and Funaro [2] for elasto-plastic shell analysis Alterations have been made in the specification of the variable yield surface, the limit surface, and the hardening law, resulting in a more accurate representation of the quasistatic elasto-plastic shell behavior. In order to generalize the model to include strain rate effects along the lines of equation (11), the plastic strain rate tensor is assumed to depend on the stress resultant intensity through the associated flow rule

$$\dot{\mathbf{e}_{ij}}^{p} = \gamma_{R} K \Phi[F(S_{ij})] \frac{\partial F(S_{ij})}{\partial S_{ij}} = \overline{\lambda} \frac{\partial F(S_{ij})}{\partial S_{ij}}$$
(38)

Recalling the work of section III, one obtains

$$\lambda = \gamma_{R} \Delta t K F(S_{ij}^{E1Tr} - E_{ijk} \ell \lambda \frac{\partial F}{\partial S_{k} \ell})$$
 (39)

Because equation (39) cannot be solved in closed form for λ , the equivalent form

$$\lambda[\gamma_R, \Delta t, K, E_{ijkl}, F(S_{ij}^{ElTr}), \frac{\partial F}{\partial S_{ij}}] = 0$$
 (40)

is solved iteratively using a modified regula falsi method.

 γ_R is a physical function which should be chosen to represent the results of multiaxial tests on plate and shell specimens of a particular material. These experiments should consist of biaxial bending and stretching tests conducted at various loading rates of concern. The present lack of such experimental data precludes the possibility of choosing this function to fit measured results. Therefore, at this time, γ_R will be chosen such that the produced stress resultants obtained via the proposed viscoplastic shell model satisfactorily represent those obtained using the through-the-thickness approach for various loading paths.

For the mild steel material [18], previously discussed, the proposed form of the function $\boldsymbol{\gamma}_{p}$ is

$$\gamma_{R} = \frac{\bar{A}_{1}[I_{N}, I_{M}^{*}]}{(F_{R})^{\bar{n}_{1}} (1 - (\frac{\sigma_{o}}{\sigma_{r}})^{2} F_{R})^{\bar{n}_{2}}}$$
(41)

where

$$\vec{A}_1[I_N, I_M^*] = A_1(\frac{I_N + A_2A_3I_M^*}{I_N + A_3I_M^*})$$
 (42)

and

$$F_R = C_1(I_N + I_N^2 - I_N^3) + C_2(I_M^*) + C_3|I_{NM}|$$
 (43)

This formulation respresents an eight parameter model

 \bar{n}_1 , \bar{n}_2 , A_1 , A_2 , A_3 , C_1 , C_2 , C_3) whose values are chosen such that the viscoplastic shell model results correspond to

the calculated through-the-thickness viscoplastic shell behavior for various loading rates and paths for the mild steel specimens. A discussion of the determination of these parameters will be given in Section V.

V COMPARISON OF THROUGH-THE-THICKNESS AND SHELL MODEL RESULTS FOR THE BEHAVIOR OF MILD STEEL

Multi-dimensional structural response involves the determination of biaxial shell forces and moments for various combinations of induced axial and bending strains. With this is mind, a series of loading cases is introduced, with each case reflecting a particular stress state feature. Figure (6) presents a listing of particular loading cases considered.

Continuing the illustrative example of mild steel behavior, the viscoplastic shell model parameters of equations (42) and (43) were determined such that the shell model results matched the through-the-thickness results for the loading paths listed in Figure (6) for loading rates (10) to (10) 1/sec.

For the mild steel considered, the determined material constants are

$$\bar{n}_1 = 3/4$$
 $\bar{n}_2 = 1/4$
 $A_1 = 20.0$
 $A_2 = 1.0$
 $A_3 = 1.0$
 $C_1 = 1.0$
 $C_2 = 0.4$
 $C_3 = 0.8$

For the loading cases analyzed, various features of the viscoplastic shell behavior are presented in Figures (7) to (23).

Figure (7) shows the variability in the axial force as a function of the applied strain rate. An increase of the yield force is seen for increasing strain rates and a corresponding reduction in yield force for decreasing strain rates. It is seen that a rise in the strain rate raises the flow stress rapidly from its previous stationary value and as straining continues at the more rapid rate, the stress approaches the value it

would have had if the entire straining process was performed at this rapid strain rate. Thus, the effects of strain rate history are erased. Experimentally, it has been shown [19] that for mild steel, strain rate history effects are minimal at ambient temperatures.

For the viscoplastic shell behavior in one dimensional bending, Figure (8) presents the moment-curvature diagrams for various loading rates. Figure (9) shows the increase of the limit force and the limit moment due to strain rate effects. One notices in Figure (9) that, at a particular loading rate, the limit moment is not as dynamically enhanced as the limit force. This is due to the variability in the strain rates through-the-thickness of the shell when deforming in a bending mode.

Loading cases three through six represent a variety of biaxial stress resultant states dominated by a particular force and/or moment. Various radial loading paths of stretching ($\Delta \epsilon$) and bending ($\Delta \epsilon$) strain increments were prescribed to produce the biaxial stress resultant states N₁ = N , N₂ = α N , M₁ = M and M₂ = β M . These loading cases were investigated for loading rates varying from (10)⁰ to (10)³ 1/sec. For the sake of brevity, the loading rate of 120 1/sec is chosen to illustrate the shell model's applicability. Each of the featured cases consists of a cyclic loading curve. The viscoplastic shell model captures the essential features and characteristics of the through-the-thickness integration calculations, as shown in Figures (10) to (14) .

was respected translated by the property of the property bearings

Figures (15) to (18) illustrate the variability in the

stress resultant limit state for the condition of equal biaxial forces and equal biaxial moments. The ratio of stretching ($\Delta \epsilon$) to bending ($\Delta \kappa$) is varied to produce various combinations of forces and moments. It is clear that the viscoplastic shell model produces a very good definition of the effect of strain rates on the dominating stress resultant quantities. The existing small deviations are seen to be independent of the loading rate and are therefore due to approximations inherent in the specification of the quasi-static yield surface.

Loading cases eight through twelve represent equal absolute magnitude biaxial forces and biaxial moments, with differing signs. Figures (19) through (23) illustrate these cases and show the good agreement which exists.

Therefore, for the various loading combinations which can occur in shell structures, it is shown that the model provides a very good definition of the viscoplastic shell behavior as determined by the through-the-thickness integration procedure. The selection of suitable but different model parameters should provide the same favorable approximations for other structural metals.

When biaxial experimental data becomes available, the model parameters can be fit to the data. It has been shown that for dynamic one dimensional bending, deviations do exist between measured moments and those computed using the through-the-thickness integration technique[20].

VI INCORPORATION OF VISCOPLATIC MODEL INTO EPSA CODE

The EPSA [3] code has been developed for the dynamic response analysis of stuctures in an acoustic medium, including both plastic collapse and/or local instability dynamic buckling) of the structure. The following is a brief description of the theoretical basis of the code:

The structural equations of motion are derived for the principle of virtual work

$$\int_{R} \{S\}^{T} \{\delta e\} dR - \int_{R} \{P\}^{T} \{\delta u\} dR + \int_{R} \rho\{\ddot{u}\} \{\delta u\} dR = 0 \quad (44)$$

with
$$\{u\} = (u_1, u_2, w)^T$$

A finite difference / finite element method is used to discretize the non-linear equations of motion. The surface of the region R is covered with a quadrilateral mesh of "j" elements, each element of area A_i .

Each arbitrarily shaped quadrilateral shell element is defined by four corner nodes, with each node having three translational and no rotational degrees of freedom. Spacial derivatives are expressed in terms of discrete nodal displacements via an irregular finite difference technique. A two dimensional Taylor series expansion in irregularly shaped meshes is employed [5]].

The integrals over region R of equation (44) are replaced by sums of integrals over A_i to obtain the following system of ordinary differential equations:

$$[M] \{\ddot{q}\} = \sum_{i=1}^{j} [\{P\}_{i} - \{F\}_{i}]$$
 (45)

where $\{q\}$ is the nodal displacement vector for the structure, [M] is the lumped mass matrix $\{P\}$ represents the vector of external forces acting on the nodes of the structure, $\{F\}$ is the vector of equivalent internal grid point forces.

The system of equations for the nodal displacements is integrated in time using an explicit central difference scheme.

The Donnell-Vlasov nonlinear kinematic equations of shell theory are used. The geometric nonlinearities are accounted for in the strain - displacement relations

1999 The second second

$$\{\dot{\mathbf{e}}\} = [\mathbf{B}] \{\dot{\mathbf{q}}\} \tag{46}$$

AND THE DESCRIPTION SOUTHERN SOUTH AND SOUTH TO SERVICE TO THE SOUTHERN THE SERVICE OF THE

The viscoplastic shell equations relate the stress resultant vector to the shell strain rate vector. These equations are solved at each time step. The magnitude of the time step is governed by the Courant criterion for the integration of the spatially discretized equations of motion.

The use of the viscoplastic shell theory results in an increase in the efficiency of the computational procedure as compared to the through-the-thickness integration technique.

This occurs because the shell theory employs nine memory parameters per element versus the 42 (6 * Number of Layers) quantities for the through-the-thickness technique. Also, the solution procedure for the shell model requires approximately 50% less computer time than the through-the-thickness technique.

VII VISCOPLASTIC SHELL ANALYSIS USING EPSA

REPRESENTATIVE EXAMPLES

The EPSA code with the inclusion of a viscoplastic shell model was used to investigate the elastic viscoplastic, large deflection, transient response of shell structures.

An analysis was performed to determine the response of a clamped-edge, mild steel, cylindrical panel subjected to impulsive loading by the sheet explosive loading technique. The geometric properties of the panel are shown in Figure (24).

Analysis of the structure by EPSA consisted of a one hundred element mesh configuration for the quarter model,

Figure (25). Initial conditions consist of initial radial velocities obtained by equating the impulse imparted by the detonated sheet to the total impulse experienced by the structure.

Figures (26) and (27) illustrate the results of two EPSA analyses, one using an elasto-plastic shell model (quasi-static yield strength), the other using a viscoplastic shell model. The viscoplastic material effects are shown to reduce the permanent deflection at the center of the specimen by twenty five percent. The peak inner fiber circumferential strain at the mid-point of the specimen is reduced from 3 percent to 2 percent due to viscoplastic shell behavior.

The second example investigated involved a stiffened cylindrical shell immersed in an acoustic medium subjected to shock loading, Figure (28). The pressure function contains an exponential decay in time and a linear spatial decay.

The EPSA quarter model of the shell and internal stiffeners

consists of a 1440 element mesh. The fluid/structure interface is accounted for by means of the Doubly Asymptotic Approximation [23].

Again, two distinct EPSA analyses were performe to isolate the effects of strain rate behavior upon the calculated response of the structure. Figure (29) shows the calculated deflection pattern across the length of the shell at the circumferential zero degree line (initial load impact position) fot the two analyses. The variability in the inner fiber circumferential strains at Frame 5 1/2 at zero degrees and 180 degrees is shown in Figure (30) for the two analyses.

VIII CONCLUSIONS

An analysis method is presented for obtaining the dynamic response of elasto-viscoplastic structures. This technique consists of the development of a viscoplastic shell theory and its incorporation into the EPSA code. The effects of viscoplastic material behavior upon the response of structures in vacuo or in an acoustic medium when subjected to transient loadings is demonstrated.

Viscoplastic material response is shown to significantly increase the resistance of shells to dynamic loadings.

Continuing development work can encompass the following:

- 1. Employ the proposed method to analyze the viscoplastic response of mild steel frame, plate and shell specimens and compare to available experimental data, [21],[22].
- Fit the shell model parameters to additional material types, i.e., titanium and high strength steels.
- Incorporate strain hardening into the material constitutive equations.
- 4. Explore the possibility of obtaining experimental biaxial stress resultants versus strain rate data so that the viscoplastic shell model parameters can be fit to such data rather than to the through-the-thickness results.

REFERENCES

CHANGE STREET, MARKET LANGUAGES (MARKET)


- 1. Perzyna, P., "Fundamental Problems in Viscoplasticity", Advances in Applied Mechanics, Vol. 9, 1966, Academic Press, pp. 243-377.
- Bieniek, M.P. and Funaro, J.R., "Elasto-Plastic Behavior of Plates and Shells", Report No. DNA 3954T, Weidlinger Associates, New York, New York, March 1976.
- 3. Atkatsh, R., Bieniek, M.P. and Baron, M.L., "Dynamic Elasto-Plastic Response of Shells in an Acoustic Medium-Theoretical Development for the EPSA Code", Technical Report No. 24, ONR Contract Nos. N00014-72-C-0119 and N00014-78-C-0820, Weidlinger Associates, New York, New York, July 1978.
- 4. Atkatsh, R., Daddazio, R.P., "Dynamic ElastoPlastic Response of Shells in an Acoustic Medium Users Manual
 for the EPSA Code", Technical Report No. 27, ONR Contract No.
 N00014-78-C-0820, Weidlinger Associates, New York, New York,
 March 1980.
- 5. Atkatsh, R., Bieniek, M.P. and Baron, M.L., "A Finite Difference Method for Bending of Plates", Computers and Structures, Vol. II, pp. 573-577, 1980.
- 6. Bingham, E.D., "Fluidity and Plasticity", McGraw-Hill, 1922.
- 7. Hohenemser, K., and Prager, W.,, Über die Ansätze der Mechanik isotroper Kontinua, Zeitschrift F. agnew. Math. U. Mech. 12, 216-226, 1932.
- 8. Cernocky, E.P. and Krempl, E., "A Theory of Viscoplasticity based on Infinitesimal Total Strain", ACTA Mechanica, Vol. 36, pp. 263-289, 1980.

- Bodner, S.R. and Partom, Y., "Constitutive Equations for Elastic-Viscoplastic Strain-Hardening Materials", J. Appl. Mech., June 1975, pp. 385-389.
- 10. Werne, R.W. and Kelly, J.M., "Rate Dependent Inelastic Behavior of Polycrystalline Solids using a Dislocation Model", Century 2 Pressure Vessels and Piping Conference, ASME, 1980.
- 11. Zirin, R.M. and Krempl, E., "A Finite Element Time Integration Method for the Theory of Viscoplasticity Based on Infinitesimal Total Strain" Century 2 Pressure Vessels and Piping Conference, ASME, 1980.
- 12. Key, S.W., "HONDO A Finite Element Computer Program for the Large Deformation Dynamic Response of Axisymmetric Solids", SLA 74-0039, 1974, Sandia Laboratories, Albuquerque, New Mexico.
- 13. Takezono, S., Tao, K., Kanezaki, K., "Elasto/Viscoplastic Dynamic Response of Axisymmetrical Shells by Overlay Model", Journal of Pressure Vessel Technology, Vol. 102, pp. 257-263, August 1980.
- 14. Lindholm, U.S., "Review of Dynamic Testing Techniques and Material Behavior", Conference on Mechanical Properties of Materials at High Rates of Strain, Institute of Physics, London, 1974.
- 15. Perrone, N., "Response of Rate Sensitive Frames to Impulse Load", Journal of Engineering Mechanics, ASCE, Feb. 1971, pp. 49-62.
- 16. Symonds, P.S. and Chon, C.T., "Large Viscoplastic Deflections of Impulsively Loaded Plane Frames", Brown University, Report N000014-0860/3, Sept. 1977.


- 17. Manjoine, M.J., "Effect of Rate of Strain on the Flow Stress of Gas Turbine Alloys at 1200 and 1500 F.", Proc. Amer. Soc. Testing Materials, Vol. 50, pp. 931-947, 1950.
- 18. Clark, D.S. and Duwez, P.E., "The Influence of Strain Rate on Some Tensile Properties of Steel", Proc. Amer. Soc. Testing Materials, Vol. 50, pp. 560-575, 1950.
- 19. Klepaczko, J. and Duffy, J., "Strain Rate History Effects in BCC Metals", Brown University Report MRLE-128, February 1981.
- 20. Aspden, R.J. and Campbell, J.D., "The Effect of Loading Rate on the Elasto-Plastic Flexure of Steel Beams", Proceedings of the Royal Society, Volume A290, pp. 266-285, 1966.
- 21. Jones, N., Uran, T.O. and Tekin, S.A., "The Dynamic Plastic Behavior of Fully Clamped Rectangular Plates", Int. J. Solids and Structures, Vol. 6, pp. 1499-1512, 1970.
- 22. Bodner, S.R. and Symonds, P.S., "Experiments on Viscoplastic Response of Circular Plates to Impulsive Loading", Brown University, Report N00014-0860/6, July 1977.
- 23. Geers, T.L., "Residual Potential and Approximate Method for Three-Dimensional Fluid-Structure Interaction Problems", J. Acoust. Soc. Amer., Vol. 49, No. 5, Part 2, 1971, pp. 1505-1510.
- 24. Drucker, D., "On Uniqueness in the Theory of Plasticity", Q. Appl. Math, Vol. 14, pp. 35-42, 1956.
- 25. Naghdi, P.M. and Murch, S.A., "On the Mechanical Behavior of Visco-elastic/Plastic Solids", Journal of Applied Mechanics, Vol. 30, pp. 321-327, 1963.

- [26] Hayashi, T. and Tanimoto, N. "Behavior of Materials under Dynamic Combined Stresses of Torsion and Tension:, IUTAM Symposium "High Velocity of Solids", Springer-Verlag N.Y. 1978.
- [27] Jones, N., Dumas, J., Grannotti, J. and Grassit, K., MIT Report No. 71-6, 1971.
- [28] Rawlings, B., "Response of Structures to Dynamic Loads", Conference of Mechanical Properties of Materials at High Rates of Strain,

 Institute of Physic, London, 1974.




BINGHAM'S ONE-DIMENSIONAL VISCOPLASTIC MODEL FIG. 1




DYNAMIC STRESS-STRAIN RELATION ELASTIC VISCOPLASTIC MATERIAL TENSION BEHAVIOR

FIG. 2




1-D YIELD FUNCTION VS. STRAIN RATE TYPICAL BEHAVIOR FOR MILD STEEL

FIG. 3




1-D YIELD STRESS VS. STRAIN RATE MILD STEEL



MULTI-DIMENSIONAL LOADING PATHS CHOSEN FOR

DETERMINATION OF VISCOPLASTIC SHELL MODEL PARAMETERS


LOADING	STRESS RESULTANTS			LOADING	
CASE	N ₁	N ₂	M ₁	I, M ₂	DESCRIPTION
					4.0.50005
	N	0	0	0	1-D FORCE
2	0	0	M	0	1-D MOMENT
3	0	0	М	βМ	2-D MOMENT
4	N	αN	М	βМ	M, DOMINATES
5	N	αN	M	βМ	N,,M,DOMINATE
6	N	αN	M	βM	N, ,M, DOMINATE
7 THRU	N	±N	M	±M	FORCES OF EQUAL MAGNITUDE
12					MOMENTS OF EQUAL MAGNITUDE




LOADING CASE No. 1

1-D FORCE

N ₁	N ₂	M ₁	M ₂
N	0	0	0



No, €o: STATIC YIELD FORCE AND STRAIN





1-D FORCE VS. STRAIN FOR €= € (€)


FIG. 7


N ₁	N ₂	M,	M ₂
0	0	M	0


Mo, Ko: STATIC YIELD MOMENT AND CURVATURE


















VISCOPLASTIC MATERIAL BEHAVIOR
1-D MOMENT VS. CURVATURE FOR VARIOUS LOADING RATES



41

CONTRACTOR TOURS CONTRACT CONTRACT CONTRACT CANDESCENT CANDESCENT CANDALOGIC CONTRACT CONTRAC


ONE DIMENSIONAL LIMIT FORCE AND MOMENT VS. LOADING RATE

SESSION CHECKEN UNDSPINE SESSION MAKERING SESSION PROPERTY

VISCOPLASTIC SHELL BEHAVIOR

MOMENT VS. CURVATURE &,= 120 1/in-sec


FIG. 10



COST ASSOCIATE. SERVICER SERVICES. COSCONO: MARGANON


VISCOPLASTIC SHELL BEHAVIOR LOADING RATE = 120 1/SEC


FIG. 11




Control of the Contro

secretaries instrument







-2.0

-4.0

0.0

CURVATURE -

2.0


4.0

--- "... AU-THE-THICKNESS INTEGRATION

VISCOPLASTIC SHELL BEHAVIOR


LOADING RATE = 120 1/SEC

FIG. 12



VISCOPLASTIC SHELL BEHAVIOR LOADING RATE = 120 1/SEC

FIG. 13





---- SHELL MODEL
---- THRU-THE-THICKNESS INTEGRATION


VISCOPLASTIC SHELL BEHAVIOR


LOADING RATE = 120 1/SEC


FIG.14











VISCOPLASTIC SHELL BEHAVIOR

LOADING RATE = 120 1/SEC

FIG.19

VISCOPLASTIC SHELL BEHAVIOR

LOADING RATE = 120 1/SEC

FIG. 20

0.0

CURVATURE Kn


4.0

8.0

-4.0

-2.0


-8.0



VISCOPLASTIC SHELL BEHAVIOR


LOADING RATE = 120 1/SEC

FIG. 21



VISCOPLASTIC SHELL BEHAVIOR
LOADING RATE = 120 1/SEC


FIG. 22



VISCOPLASTIC SHELL BEHAVIOR
LOADING RATE = 120 1/SEC

FIG. 23

NON-LINEAR TRANSIENT RESPONSE OF CYLINDRICAL PANEL STUDY OF VISCO-PLASTIC EFFECTS



MATERIAL PROPERTIES

DENSITY:

7.33 × 10 4 LB-SEC 2/ IN 4

CURVATURE:

YOUNG'S MODULUS:

0.0877 30×10⁶ PSI


POISSON'S RATIO:

0.3

STATIC YIELD STRENGTH: 40,000 PSI

FIG. 24

EPSA FINITE ELEMENT MODEL (1/4 PANEL)




INITIAL NORMAL VELOCITIES SPECIFIED FOR LOADED REGION \$\ddq_z = 2250 \text{ in/sec}

FIG. 25


PANEL NON-LINEAR VISCOPLASTIC RESPONSE OF CYLINDRICAL SUBJECTED TO TRANSIENT LOADING

weekens mountain, remember, recovery, whitever



PERMANENT DEFLECTION ALONG CENTERLINE OF STRUCTURE

FIG. 26



THE STATE OF THE STATE AND THE STATE OF THE

FIG. 27

THE RESERVE OF THE PROPERTY OF THE PARTY OF

STIFFENED CYLINDRICAL SHELL IMMERSED IN AN ACOUSTIC MEDIUM






FIG. 28







STATE OF THE PROPERTY OF THE PARTY OF THE PA

INNER FIBER HOOP STRAIN
FIG. 30

DISTRIBUTION LIST

DEPARTMENT OF DEFENSE	DEPARTMENT OF THE ARMY (Continued)
Assistant to the Secretary of Defense Atomic Energy ATIN: Exec Asst	Deputy Chief of Staff for Ops & Plans ATTN: DAMO-NC, Nuc Chem Dir
Defense Advanced Rsch Proj Agency ATTN: TIO	Deputy Chief of Staff for Rsch Dev & Acq ATTN: DAMA
Defense Intelligence Agency ATTN: DB-4C2	Engineer Studies Ctr ATTN: DAEN-FES, LTC Hatch
ATTN: DB-4C2, C. Wiehle ATTN: DT-1C ATTN: DT-2 ATTN: RTS-2A	Harry Diamond Labs ATTN: DELHD-NW-P, 20240 ATTN: DELHD-TA-L, 81100
ATTN: DB-4C3 ATTN: DB-4C, Rsch, Phys Vuln Br ATTN: DB-4C1	USA Concepts Analysis Agency ATTN: CSSA-ADL
Defense Nuclear Agency ATTN: SPSS	USA Engineer Ctr & Ft Belvoir ATTN: ATZA-DTE-ADM
ATTN: STSP 4 cy ATTN: TITL	USA Engineer School ATTN: ATZA-CDC
Defense Technical Information Ctr 12 cy ATTN: DD	USA Engr Waterways Exper Station ATTN: R. Whalin ATTN: WESSE ATTN: WESSD, J. Jackson
Field Command Defense Nuclear Agency Det 1 Lawrence Livermore Lab ATTN: FC-1	ATTN: J. Strange ATTN: J. Zelasko ATTN: F. Brown ATTN: Library
Field Command Defense Nuclear Agency ATTN: FCPR	ATTN: WESSA, W. Flathau ATTN: WESSS, J. Ballard
ATTN: FCT ATTN: FCTX ATTN: FCTT, G. Ganong	USA Foreign Science & Tech Ctr ATTN: DRXST-SD
ATTN: FCTT, W. Summa ATTN: FCTXE	USA Mat Cmd Proj Mgr for Nuc Munitions ATTN: DRCPM-NUC
Field Command Test Directorate ATTN: FCTC	USA Material & Mechanics Rsch Ctr ATTN: DRXMR, J. Mescall ATTN: Tech Library
Interservice Nuclear Weapons School ATTN: TTV Joint Strat Tgt Planning Staff	USA Materiel Dev & Readiness Cmd ATTN: DRCDE-D, L. Flynn ATTN: DRXAM-TL
ATTN: NRI-STINFO Library ATTN: JLA, Threat Appl Div ATTN: JLTW, R. Autenberg ATTN: JLTW-2	USA Nuclear & Chemical Agency ATTN: Library
ATTN: DOXT ATTN: XPFS	USA War College ATTN: Library
Under Secretary of Defense for Rsch & Engrg ATTN: Strat & Space Sys (OS)	USA Military Academy ATTN: Doc Library
DEPARTMENT OF THE ARMY	USA Missile Cmd ATTN: Doc Sec
BMD Advanced Technology Ctr ATTN: ICRDABH-X ATTN: ATC-T	ATTN: DRSMI-RH DEPARTMENT OF THE NAVY
Chief of Engineers ATTN: DAEN-RDL ATTN: DAEN-MPE-T	Marine Corp Dev & Ed Cmd ATTN: DO91, J. Hartneady

DEPARTMENT OF THE NAVY (Continued)	DEPARTMENT OF THE NAVY (Continued)
David Taylor Naval Ship R&D Ctr	Naval Surface Wpns Ctr
ATTN: Code L42-3	ATTN: Code F34
ATTN: Code 1700, W. Murray	ATTN: Code R13
ATTN: Code 1844	ATTN: Code R10
ATTN: Code 177, E. Palmer	ATTN: Code U401, M. Kleinerman
ATTN: Code 172	ATTN: Code R14
ATTN: Code 1770.1	ATTN: Code F31
ATTN: Code 174	ATTN: Code R14
ATTN: Code 2740	ATTN: Code R15
ATTN: Code 1740.4	
ATTN: Code 1740, R. Short	Naval Surface Weapons Ctr
ATTN: Code 1740, R. Short ATTN: Code 1/3	ATTN: W. Wishard
ATTN: Code 1!	ATTN: Tech Library & Info Svcs Br
ATTN: Code 1740.5	
ATTN: Code 1740.6	Naval War College
ATTN: Code 1740.1	ATTN: Code E-11, Tech Svc
Marine Corps	Naval Wpns Ctr
ATTN: POM	ATTN: Code 233
	ATTN: Code 266, C. Austin
Naval Civil Engineering Lab	ATTN: Code 3263, J. Bowen
ATTN: Code L51, J. Crawford	
	Naval Weapons Evaluation Facility
Naval Coastal Systems Lab	ATTN: G. Binns
ATTN: Code 741	ATTN: Code 10
	ATTN: Code 210
Naval Electronic Systems Cmd	ATTN: R. Hughes
ATTN: PME 117-21	
	Naval Weapons Support Ctr
Naval Explosive Ord Disposal Fac	ATTN: Code 70553, D. Moore
ATTN: Code 504, J. Petrousky	
	New London Lab
Naval Facilities Engineering Cmd	Naval Underwater Systems Ctr
ATTN: Code 048	ATTN: Code 4494, J. Patel
	ATTN: Code 4492, J. Kalinowski
Naval Material Cmd	
ATTN: MAT 08T-22	Newport Lab
	Naval Underwater Systems Ctr
Naval Ocean Systems Ctr	ATTN: Code EM
ATTN: Code 013, E. Cooper	ATTN: Code 363, P. Paranzino
ATTN: Code 4471	
	Office of the Deputy Chief of Naval Ops
Naval Postgraduate School	ATTN: OP 987
ATTN: Code 69NE	ATTN: NOP 982, Tac Air Srf & EWDEV Div
ATTN: Code 1424, Library	ATTN: NOP 981
ATTN: Code 69SG, Y Shin	ATTN: NOP 654, Strat Eval & Anal Br
	ATTN: OP 098T8
Naval Research Lab	ATTN: OP 982E, M. Lenzini
ATTN: Code 8403, R. Belsham	ATTN: OP 957E
ATTN: Code 8440, G. O'Hara	ATTN: NOP 953, TAC Readiness Div
ATTN: Code 6380	ATTN: OP 37
ATTN: Code 8100	ATTN: OP 225
ATTN: Code 8301	ATTN: OP O3EG
ATTN: Code 8406	ATTN: OP 21
ATTN: Code 2627	ATTN: NOP 951, ASW Div
ATTN: Code 8445	ATTN: OP 605D5
ATTN: Code 8404, H. Pusey	ATTN: OP 981N1
,,,,,,,, .	ATTN: OP 223
Naval Sea Systems Cmd	
ATTN: SEA-033	Office of Naval Research
ATTN: SEA-323	ATTN: Code 474, N. Perrone
ATTN: SEA-06J, R Lane	
ATTN: SEA-09G53	Strategic Systems Project Office
ATTN: SEA-55X1	ÄTTN: NSP-272
ATTN: SEA-08	ATTN: NSP-43
ATTN: SEA-0351	ATTN: NSP-273
ATTN: SEA-9931G	
111 F	

TO THE THE PARTY OF THE PARTY OF THE PROPERTY OF THE PARTY OF THE PART

DEPARTMENT OF THE AIR FORCE

Air Force Institute of Technology

ATTN: Cmdr ATTN: Library

Air Force Systems Cmd ATTN: DLW

Air Force Wpns Lab

ATTN: NTES-G, S. Melzer
ATTN: NTE, M. Plamondon
ATTN: NTES-C, R. Henny
ATTN: SUL
ATTN: NTED

Assistant Chief of Staff Intelligence ATTN: IN

Ballistic Missile Office ATTN: DEB

Deputy Chief of Staff Research, Development, & Acq

ATTN: AFRDQI ATTN: R. Steere

Deputy Chief of Staff Logistics & Engrg

Foreign Technology Division ATTN: NIIS Library ATTN: TQTD ATTN: SQBG

ATTN: SDBF, S. Spring

Rome Air Development Ctr

ATTN: RBES, R. Mair ATTN: Cmdr ATTN: TSLD

Strategic Air Command

ATTN: NRI-STINFO Library

OTHER GOVERNMENT AGENCIES

Central Intelligence Agency ATTN: OSWR/NED ATTN: OSR/SE/F

Department of the Interior US Geological Survey

ATTN: D. Roddy

Federal Emergency Management Agency

ATTN: Asst Assoc Dir for Rsch, J. Kerr ATTN: W. Chipman/NP-CP

NASA

ATTN: F. Nichols ATTN: R. Jackson

US Nuclear Regulatory Commission
ATTN: R. Whipp for Div Sec L. Shao

NATO

NATO School (SHAPE)

ATTN: US Doc Ofcr

DEPARTMENT OF ENERGY

Department of Energy ATTN: CTID

Department of Energy ATTN: OMA/RD&T

Department of Energy

ATTN: Doc Con for Tech Library

DEPARTMENT OF ENERGY CONTRACTORS

University of California Lawrence Livermore National Lab ATTN: S. Erickson

Los Alamos National Lab

ATTN: R. Whitaker ATTN: MS530, G. Spillman ATTN: Reports Library ATTN: M/S634, T. Dowler ATTN: R. Sanford ATTN: MS 670, J. Hopkins

Oak Ridge National Lab

ATTN: Civil Def Res Proj ATTN: Central Rsch Library

Sandia National Lab

ATTN: Tech Lib 3141 ATTN: L. Vortman

Sandia National Labs, Livermore ATTN: Library & Sec Class Div

DEPARTMENT OF DEFENSE CONTRACTORS

Applied Research Associates, Inc ATTN: D. Piepenburg

Applied Research Associates, Inc ATTN: B. Frank

BDM Corp

ATTN: T. Neighbors ATTN: A. Lavagnino ATTN: Corp Library

California Institute of Technology ATTN: T. Ahrens

California Research & Technology, Inc ATTN: M. Rosenblatt ATTN: S. Schuster ATTN: Library ATTN: K. Kreyenhagen

Columbia University ATTN: H. Bleich ATTN: F. Dimaggio

University of Denver ATTN: Sec Ofcr for J. Wisotski

Electric Power Research Institute ATTN: G. Sliter

Electro-Mech Systems, Inc ATTN: R. Shunk

DEPARTMENT OF DEFENSE CONTRACTORS (Continued)

General Dynamics Corp ATTN: J. Miller ATTN: J. Mador ATTN: M. Pakstys

Kaman AviDyne

CONTRACT CONTRACTOR OF THE PROPERTY OF THE PRO

ATTN: R. Ruetenik ATTN: G. Zartarian ATTN: Library ATTN: N. Hobbs

Kaman Sciences Corp ATTN: Library ATTN: F. Shelton

Kaman Sciences Corp ATTN: D. Sachs

Kaman Tempo ATTN: DASIAC

Karagozian and Case ATTN: J. Karagozian

Lockheed Missiles & Space Co, Inc ATTN: Tech Info Ctr ATTN: T. Geers ATTN: B. Almroth

Lockheed Missiles & Space Co, Inc ATTN: TIC-Library

M&T Co

ATTN: D. McNaight

Management Science Associates ATTN: K. Kaplan

McDonnell Douglas Corp ATTN: R. Halprin

NKF Engrg Associates, Inc ATTN: R. Belsheim

Pacific-Sierra Research Corp ATTN: H. Brode, Chairman SAGE

Pacifica Technology ATTN: R. Bjork ATTN: G. Kent

ATTN: A. Kushner

Physics International Co ATTN: L. Behrmann ATTN: F. Sauer

ATTN: J. Thomsen ATTN: E. Moore ATTN: Tech Library

DEPARTMENT OF DEFENSE CONTRACTORS (Continued)

Physics Applications, Inc ATTN: C. Vincent

S-CUBED

ATTN: T. Cherry ATTN: R. Sedgewick ATTN: D. Grine ATTN: T. Riney ATTN: Library ATTN: K. Pyatt ATTN: T. McKinley

Science Applications, Inc ATTN: Tech Library

Southwest Research Institute

ATTN: A. Wenzel ATTN: W. Baker

SRI International

ATTN: G. Abrahamson ATTN: W. Wilkinson ATTN: A. Florence

Teledyne Brown Engineering ATTN: J. Ravenscraft

Tetra Tech, Inc ATTN: L. Hwang

TRW Electronics & Defense Sector

ATTN: P. Bhuta ATTN: A. Feldman ATTN: N. Lipner ATTN: Tech Info Ctr ATTN: D. Jortner ATTN: B. Sussholtz

TRW Electronics & Defense Sector

ATTN: P. Dai ATTN: F. Pieper ATTN: E. Wong ATTN: G. Hulcher

Weidlinger Assoc, Consulting Engrg ATTN: J. McCormick ATTN: M. Baron 4 cy ATTN: R. Atkatsh 4 cy ATTN: M. Bieniek 4 cy ATTN: I. Sandler

Weidlinger Associates ATTN: J. Isenberg

END

FILMED

9-83

DTIC